

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-171014

(43)Date of publication of application : 09.07.1993

(51)Int.Cl.

C08L 67/02

C08J 5/18

C08K 3/22

D01F 6/84

D01F 6/84

D01F 6/92

(21)Application number : 03-343820

(71)Applicant : TORAY IND INC

(22)Date of filing : 26.12.1991

(72)Inventor : AOYAMA MASATOSHI  
YOSHIDA MINORU  
SUZUKI MASARU

## (54) POLYESTER COMPOSITION

## (57)Abstract:

PURPOSE: To prepare a polyester compsn. which does not clog a polymer filter in the molding step and is useful for preparing a film or fiber excellent in abrasion resistance by compounding a specific arom. polyester with a particulate zirconium oxide.

CONSTITUTION: An arom. polyester obtd. by copolymerizing at least one compd. having a sulfonic acid (or metal sulfonate) group with other necessary comonomers (e.g. one obtd. from dimethyl 5-sodiumsulfoisophthalate, dimethyl terephthalate, and ethylene glycol) is compounded with a particulate zirconium oxide pref. having a mean particle diameter of 0.005-3 $\mu$ m, still pref. 0.005-0.2 $\mu$ m.

## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]